

AD

66-382

COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS



DISTRIBUTION STATEMENT A

Approved for public release;
Distribution Unlimited

TECHNICAL REPORT

By

John A. Williams

January 1966

DTIC QUALITY INSPECTED 1

U. S. ARMY WEAPONS COMMAND
ROCK ISLAND ARSENAL
RESEARCH & ENGINEERING DIVISION

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
DEPARTMENT OF DEFENSE
ASTICS TECHNICAL EVALUATION CENTER
PICATINNY ARSENAL, DOVER, N. J.

19960419 062

PLASTIC 8/2/78

DISPOSITION INSTRUCTIONS:

Destroy this report when it is no longer needed. Do not return it to the originator.

DISCLAIMER:

The findings of this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of commercial products in this report does not constitute an official indorsement or approval of such products.

AD

U. S. ARMY WEAPONS COMMAND

ROCK ISLAND ARSENAL

RESEARCH & ENGINEERING DIVISION

TECHNICAL REPORT

66-382

COAGENTS FOR IMPROVING ELASTIC RECOVERY
IN POLYESTER URETHANE ELASTOMERS

By

John A. Williams
Laboratory Branch

January 1966

DA #1C024401A329

AMS Code 5025.11.295

Distribution of this document is unlimited.

ABSTRACT

A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery.

Several coagents evaluated with high levels (6 pphr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pphr) of peroxide produced vulcanizates with improved elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone.

TABLE OF CONTENTS

	<u>Page No.</u>
Title Page	1
Abstract	2
Table of Contents	3
Problem	4
Background	4
Approach	4
Results and Discussion	5
Conclusions	11
Recommendations	11
Distribution	13
DD Form 1473 (Document Control Data - R&D)	20

PROBLEM

To discover and evaluate new curing systems for polyester urethanes in an attempt to produce vulcanizates with improved physical properties.

BACKGROUND

It is well known that the physical properties of an elastomeric vulcanizate depend to some extent on the type of curing system. For example, the air aging resistance of butadiene/styrene or butadiene/acrylonitrile rubber cured with sulfur and accelerator can be improved by changing to a thiuram-thiazole curing system. Butyl rubber cured with a phenolic resin has better heat resistance than when cured with sulfur-accelerator combinations.

The main deficiency in some of the peroxide cured polyester urethane vulcanizates is their poor resistance to high temperatures. Genthane S cured with 6 pphr dicumyl peroxide (40% active) produces a vulcanizate with a compression set of ninety five percent after seventy hours at 250°F. This deficiency demonstrates the need in polyester urethanes for a curing system to improve their resistance to high temperatures.

Dicumyl peroxide is a highly active crosslinking agent. This high activity enables this peroxide to activate other chemical agents that have been incorporated into a rubber compound. Such agents are referred to as coagents. It is the intent of this work to discover and evaluate new coagents of peroxide that will produce polyester urethane vulcanizates with improved high temperature resistance.

High peroxide curing systems are now needed to produce polyester urethane vulcanizates with good elastic recovery. High levels of peroxide are known to produce a residue in the rubber (acetophenone) which is detrimental to the strength of bonds formed during the vulcanization bonding of rubber to metal. Effective coagents of peroxide vulcanization could enable the peroxide level to be lowered without loss of properties thereby leading to improved bond strength.

APPROACH

The dicumyl peroxide and coagents were incorporated into portions of the polyester urethane carbon black masterbatch on a 2-1/2" X 7" two roll mill.

Vulcanizates with 3 and 6 pphr dicumyl peroxide were used as controls. The coagents were incorporated in various amounts in an attempt to find the concentration that would give optimum physical properties. The coagents giving optimum physical properties with 6 pphr dicumyl peroxide were evaluated with 3 pphr dicumyl peroxide in an attempt to produce vulcanizates with low peroxide content.

RESULTS AND DISCUSSION

A large number of potential coagents of peroxide were evaluated in two polyester urethanes, Genthane S and SR, with results shown in Tables I, II, III and IV. Only the coagent concentrations that produce optimum physical properties are listed. A cure temperature of 320°F. produced vulcanizates with optimum physical properties.

Table I gives the results of the evaluation of Genthane S cured with 6 pphr dicumyl peroxide and various coagents. The greatest affect on physical properties was obtained with the combination of triallyl cyanurate and polycarbodiimide. Compression set was reduced from 64 to 24 percent at 212°F. and from 95 to 46 percent at 250°F. Triallyl cyanurate without polycarbodiimide also produces a vulcanizate with good elastic recovery.

Another coagent that produced a vulcanizate with low compression set was diallyl carbonate. The addition of polycarbodiimide creates a synergistic effect demonstrated by reduced compression set at 212°F. and 250°F. Tensile strength was increased by the polycarbodiimide addition but the other stress-strain properties were only slightly affected.

Polycarbodiimide incorporated in a Genthane S compound without other coagents produces a vulcanizate with improved stress-strain properties and a significantly improved compression set at 212°F. and 250°F.

All of the coagents listed produced vulcanizates with increased crosslinking shown by increased modulus and hardness with lowered elongation and compression set.

Table II gives the evaluation of vulcanizates of Genthane SR cured with 6 pphr dicumyl peroxide and various coagents. A combination of diallyl adipate and polycarbodiimide produced the best vulcanizate for elastic recovery. Compression set was reduced from 30 to 9 percent at 212°F. and from 66 to 31 percent at 250°F. Diallyl adipate without polycarbodiimide also produced good elastic recovery. Stress-strain properties suffered

TABLE I
EVALUATION OF COAGENTS IN THE PEROXIDE VULCANIZATION OF GENTHANE S

Ingredients	Parts By Weight															
	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
Genthan S	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
Stearic Acid	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Philblack A	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30
DiCup 40C	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6
Triallyl Cyanurate	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
Poly carbodiimide	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
Diallyl Itaconate																
N,N'-p-Benzidene																
3,3'-dichloro-bis-maleimide																
Diallyl Adipate																
Dimer-of-Toluene-2,4-diisocyanate																
Ethylene Dimethacrylate																
Trimethylol-propane-Trimethacrylate																
N,N'-M-phenylene-bismaleimide																
Tetra-allyloxy-propane																
Methylene-di-p-phenyl diisocyanate																
3,3'-Dimethoxy-4,4'-biphenyl diisocyanate																
Diallyl Carbonate																
Physical properties																
Tensile (psi)	3750	3420	3030	3070	3950	3600	4020	3490	4450	3470	3730	3820	4110	3440	3540	3540
Modulus (100%)	290	560	540	850	310	310	410	360	540	410	500	450	470	320	370	450
Modulus (200%)	570	2580	2770	-	900	800	1780	1120	1450	1310	1350	1370	1790	970	1010	1470
Modulus (300%)	1570	-	-	-	2070	1680	-	2280	2680	2320	2540	-	-	2140	2160	3030
Elongation (%)	520	235	210	135	505	560	320	375	500	435	400	305	310	450	400	370
Hardness-Shore A	64	74	71	75	67	65	71	69	75	71	71	69	71	68	70	75
Compression set																
70 hrs/2120°F.	64	24	31	36	40	39	41	39	39	36	42	46	48	56	57	60
70 hrs/2500°F.	95	46	56	69	72	79	79	81	92	94	91	91	86	91	89	91

TABLE II
EVALUATION OF COAGENTS IN THE PEROXIDE VULCANIZATION OF GENTHANE SR

Ingredients	Parts by Weight																							
	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
Gentane SR	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Stearic Acid	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30
Philblack A	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6
DiCup 40C	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
Diallyl Adipate	3	3																						
polycarbodiimide	4																							
N,N'-M-phenylene bismaleimide																								
Triallyl Cyanurate																								
Ethylene Dimethacrylate																								
Tetra-Allyloxy-propane																								
Diallyl Itaconate																								
Dimer of Toluene																								
2,4-diisocyanate																								
Trimethylol-propane trimethacrylate																								
Methylene di-p-phenyl diisocyanate																								
3,3'-Dimethoxy 4,4'-biphenyl diisocyanate																								
Diallyl Carbonate																								
Physical Properties																								
Tensile (psi)	4280	2830	2300	3080	3290	3870	3100	2560	4130	2620	3330	3440	3770	3710	3700	2930	3860	4160	2910	2820				
Modulus (100%)	340	440	720	390	600	320	520	610	390	350	330	530	560	430	370	840	540	380	520	570				
(200%)	950	1770	2230	1730	2380	1510	1830	-	1080	1150	960	1370	1720	1500	870	-	1690	1140	1610	1940				
(300%)	2230	-	-	-	-	3430	-	-	2260	2290	2100	3210	3130	2960	2890	-	3160	2760	-	-				
Elongation (%)	475	245	205	280	245	385	280	195	485	450	440	320	350	360	580	160	365	440	310	260				
Hardness (Shore A)	67	73	75	73	73	67	72	74	68	68	65	67	78	70	69	77	72	70	70	70				
Compression Set																								
70 hrs/212°F.	30	9	14	16	16	17	21	22	23	25	25	26	31	32	33	36	43	46	16	18				
70 hrs/250°F.	66	31	42	39	49	51	50	50	54	54	58	57	67	62	66	69	79	81	41	41				

TABLE III

EVALUATION OF COAGENTS IN THE VULCANIZATION OF
GENTHANE S AT LOW PEROXIDE CONCENTRATION

Ingredients	Parts By Weight									
	100	100	100	100	100	100	100	100	100	100
Genthane S	0.2	0.22	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Stearic Acid	30	30	30	30	30	30	30	30	30	30
Philblack A	3	3	3	3	3	3	3	3	3	3
Dicumyl peroxide (40% active)										
Diallyl Carbonate		1.5		1.5		1.5				
Triallyl Cyanurate			1.5				1.5			
Polycarbodiimide		2		2				2		
Diallyl Itaconate										1.5
Physical Properties										
Tensile (psi)	2940	3930	3460	3560	3280	3720	3510			
Modulus (100%)	140	350	330	230	290	240	270			
(200%)	270	900	810	620	720	480	570			
(300%)	590	1810	1890	1300	1670	1120	1300			
Elongation (%)	950	590	515	670	500	810	710			
Hardness (Shore A)	60	67	66	62	66	64	65			
Compression Set										
70 hrs/212°F.	100	40	41	75	60	56	66			
70 hrs/250°F.	114	83	70	105	88	103	114			

TABLE IV

EVALUATION OF COAGENTS IN THE VULCANIZATION OF
GENTHANE SR AT LOW PEROXIDE CONCENTRATION

Ingredients													
Genthane SR	100	100	100	100	100	100	100	100	100	100	100	100	100
Stearic acid	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Philblack A	30	30	30	30	30	30	30	30	30	30	30	30	30
Dicumyl peroxide (40% active)	3	3	3	3	3	3	3	3	3	3	3	3	3
Diallyl carbonate		1.5					1.5						
Polycarbodiimide		2						2					2
Triallyl Cyanurate		1.5					1.5						
Diallyl Adipate			1.5						1.5				
N,N'-M-phenylene bismaleimide								0.5					0.5
Physical Properties													
Tensile (psi)	3250	3330	2950	3430	3610	3170	3350	2950	3180	3320			
Modulus (100%)	150	340	270	290	340	270	280	290	230	230			
Modulus (200%)	360	800	780	710	820	770	560	660	570	520			
Modulus (300%)	850	1700	1680	1600	1840	1790	1250	1310	1500	1110			
Elongation (%)	810	590	465	635	565	450	680	600	600	765			
Hardness-Shore A	60	67	63	65	63	63	62	65	62	62			
Compression Set													
70 hrs/212°F.	55	27	30	32	35	37	33	40	47	47			
70 hrs/250°F.	85	57	64	62	62	69	69	71	75	80			

from the increased crosslinking caused by these coagents.

N,N'-M-phenylene bismaleimide at 1 pphr produced a vulcanizate with excellent elastic recovery. As the concentration of this bismaleimide increases the physical properties begin to deteriorate. Polycarbodiimide addition improves elastic recovery.

Triallyl cyanurate and diallyl carbonate each produce vulcanizates with good elastic recovery, but only triallyl cyanurate shows improvement with the addition of polycarbodiimide. Without other coagents polycarbodiimide demonstrates improved compression set without affecting the stress-strain properties.

Diisocyanates, dimethacrylates, and diallyl itaconate offer very little improvement in the physical properties of a Genthane SR vulcanizate.

Hydroquinones, quinones, melamines, dioximes and phenol compounds evaluated as potential coagents in Genthane S and SR resulted in weakened or completely destroyed cures.

The coagents which proved effective with 6 pphr dicumyl peroxide were evaluated with 3 pphr dicumyl peroxide. If a good vulcanizate cured with low peroxide can be found it may eliminate some of the problems in rubber to metal bonding caused by high peroxide cures. The results of this evaluation are listed in Tables III and IV.

Triallyl cyanurate and polycarbodiimide proved to be the most effective combination in the low peroxide vulcanization of Genthane S. This vulcanizate gives stress-strain properties comparable to a vulcanizate cured with 6 pphr peroxide and lower compression set.

Diallyl carbonate provided improvement in the physical properties of a low peroxide cured Genthane S vulcanizate but was not as effective as triallyl cyanurate.

Diallyl carbonate proved to be the most effective coagent evaluated with 3 pphr dicumyl peroxide in a Genthane SR vulcanizate. With polycarbodiimide added, compression sets of 27 percent at 212°F. and 57 percent at 250°F. were obtained. These compression sets are better than those obtained with a vulcanizate cured with 6 pphr dicumyl peroxide, but stress-strain properties are not as good.

Triallyl cyanurate, diallyl adipate, and N,N'-M-phenylene bismaleimide produce low peroxide vulcanized Genthane SR with good physical properties.

Table V lists a series of Genthane S and SR vulcanizates cured with 3,6,8 and 10 pphr dicumyl peroxide. Physical properties improved with increasing peroxide concentration, but at ten pphr peroxide, the compression set specimens displayed crumbled edges when tested at 212°F. and 250°F. These high peroxide cured vulcanizates do not display the good elastic recovery obtained with the peroxide coagent cured vulcanizates.

CONCLUSIONS

Diallyl esters of dibasic acids when used as coagents of peroxide produce excellent elastic recovery in the Genthane SR vulcanizates.

Diallyl esters of dibasic acids were not as effective in Genthane S as they were in Genthane SR.

Triallyl cyanurate offered excellent improvement in the elastic recovery of both Genthane S and SR.

N,N'-M-phenylene bismaleimide is an effective coagent at low concentrations in Genthane SR, but is ineffective as a coagent in Genthane S.

Polycarbodiimide in combination with these coagents or by itself in peroxide vulcanization demonstrates the ability to improve compression set with little effect on the stress-strain properties.

Attempts to duplicate the good compression set obtained with these coagents using a high peroxide concentration alone failed.

RECOMMENDATIONS

Coagents showing most promise in this work notably diallyl esters of dibasic acids, triallyl cyanurate and N,N'-M-phenylene bismaleimide should be examined in other elastomers (including polyether based polyurethanes) in order to explore the generality of their application. Also, related family members of these chemical classes should be investigated.

High peroxide curing systems in polyester polyurethanes create the problems of poor rubber to metal bonding and strong residual order. A good low peroxide curing system or a curing system void of peroxide should be sought.

TABLE V

**VULCANIZATION OF GENTHANE S AND SR AT
VARIOUS PEROXIDE CONCENTRATIONS**

Ingredients

Genthane S	100	100	100	100
Stearic acid	0.2	0.2	0.2	0.2
Philblack A	30	30	30	30
DiCup 40C	3	6	8	10

Physical Properties

Tensile (psi)	2940	3750	4000	2950
Modulus (100%)	140	290	400	1190
(200%)	270	570	1150	1710
(300%)	590	1570	3090	-
Elongation (%)	950	520	410	250
Hardness (Shore A)	60	64	67	70

Compression Set

70 hrs/212°F.	100	64	53	41 crumbled edges
70 hrs/250°F.	114	95	85	74 crumbled edges

Genthane SR	100	100	100	100
Stearic acid	0.2	0.2	0.2	0.2
Philblack A	30	30	30	30
DiCup 40C	3	6	8	10

Physical Properties

Tensile (psi)	3250	4280	3860	3740
Modulus (100%)	150	340	430	560
(200%)	360	950	1410	2300
(300%)	850	2230	3100	-
Elongation (%)	810	475	370	270
Hardness (Shore A)	60	67	71	72

Compression Set

70 hrs/212°F.	55	30	23	21 crumbled edges
70 hrs/250°F.	85	66	57	46 crumbled edges

DISTRIBUTION

No. of Copies

A. Department of Defense

Office of the Director of Defense
Research & Engineering
ATTN: Mr. J. C. Barrett
Room 3D-1085, The Pentagon
Washington 25, D. C.

1

Commander
Defense Documentation Center
ATTN: TIPDR
Cameron Station
Alexandria, Virginia 22314

20

B. Department of the Army - Technical Services

Commanding General
U. S. Army Materiel Command
ATTN: AMCRD-RC
Washington, D. C. 20315

1

Commanding Officer
U. S. Army Coating and Chemical Laboratory
ATTN: Dr. C. Pickett
Technical Library
Aberdeen Proving Ground, Maryland 21005

1

1

Commanding General
U. S. Army Tank Automotive Center
ATTN: SMOTA-REM.2
SMOTA-REM.3
Warren, Michigan 48090

1

1

Commanding General
U. S. Army Weapons Command
ATTN: AMSWE-RD
AMSWE-PP
Rock Island Arsenal
Rock Island, Illinois

1

1

Commanding Officer
U. S. Army Production Equipment Agency
ATTN: AMXPE
Rock Island Arsenal
Rock Island, Illinois

1

DISTRIBUTION

No. of Copies

Commanding General
U. S. Army Missile Command
ATTN: Documentation & Technical Information Branch 2
Mr. R. E. Ely, AMSMI-RRS 1
Mr. R. Fink, AMSMI-RKX 1
Mr. W. K. Thomas, AMSMI 1
Mr. E. J. Wheelahan, AMSMI-RSM 1
Redstone Arsenal, Alabama 35809

Commanding Officer
Frankford Arsenal
ATTN: SMUFA-1330 1
Library-0270 1
Philadelphia, Pa. 19137

Commanding Officer
U. S. Army Materials Research Agency
Watertown Arsenal
ATTN: RPD
Watertown, Mass. 02172 1

Commanding Officer
Picatinny Arsenal
ATTN: Plastics & Packaging Lab. 1
PLASTEC 1
Dover, New Jersey 07801

Commanding Officer
Springfield Armory
ATTN: SWESP-TX
Springfield, Mass. 01101 1

Commanding Officer
Watertown Arsenal
ATTN: SMIWT-LX
Watertown, Mass. 02172 1

Commanding Officer
Watervliet Arsenal
ATTN: SWEWV-RDR
Watervliet, New York 12189 1

Commanding General
U. S. Army Munitions Command
Picatinny Arsenal
Dover, New Jersey 07801 1

DISTRIBUTION

No. of Copies

Commanding Officer
U. S. Army Environmental Health Laboratory
Army Chemical Center, Maryland 1

Commanding Officer
U. S. Army Chemical Warfare Laboratories
ATTN: Technical Library
Army Chemical Center, Maryland 1

Commanding Officer
Tobyhanna Army Depot
ATTN: SMC Packaging and Storage Center
Tobyhanna, Pennsylvania 18466 1

Commanding Officer
U. S. Army Engineer R&D Laboratories
ATTN: Chemistry Research Section,
Materials Branch
Fort Belvoir, Virginia 1

Commanding Officer
U. S. Army Electronics R&D Laboratories
ATTN: Mr. Dan Lichtenstein-PEE
Materials Branch 1
Fort Monmouth, New Jersey 07703 1

Commanding General
Quartermaster R&D Command
ATTN: Clothing & Organic Materials Div.
Natick, Massachusetts 01762 1

Commanding Officer
U. S. Army Prosthetics Research Laboratory
Forest Glen, Maryland 1

Director
Joint Military Packaging Training Center
ATTN: AMXPT-PT
Aberdeen Proving Ground, Maryland 21005 1

Department of the Army - Other Army Agencies

U. S. Army Reactor Branch
Division of Reactor Development
Atomic Energy Commission
Washington 25, D. C. 1

DISTRIBUTION

No. of Copies

Commander
U. S. Army Research Office
Arlington Hall Station
Arlington 12, Virginia

1

Commanding Officer
U. S. Army Research Office (Durham)
Box CM, Duke Station
Durham, North Carolina 27706

1

Chief of Research & Development
U. S. Army Research & Development
Liaison Group
ATTN: Dr. B. Stein
APO 757
New York, N. Y.

1

Commanding Officer
U. S. Army Aviation School
ATTN: Office of the Librarian
Fort Rucker, Alabama

1

C. Department of the Navy

Chief
Bureau of Naval Weapons
Department of the Navy
ATTN: RMMP
Room 2225, Munitions Building
Washington 25, D. C.

1

Commander
Department of the Navy
Office of Naval Research
ATTN: Code 423
Washington 25, D. C.

1

Chief
Department of the Navy
Bureau of Ships
ATTN: Code 344
Washington 25, D. C.

1

Commander
Department of the Navy
Special Projects Office
ATTN: SP 271
Washington 25, D. C.

1

DISTRIBUTION

No. of Copies

Commander
U. S. Naval Ordnance Laboratory
ATTN: Code WM
White Oak
Silver Spring, Maryland 20910

1

Chief
Bureau of Supplies & Accounts
ATTN: SANDA 44
Department of the Navy
Washington, D. C.

1

Director
Aeronautical Materials Laboratory
Naval Air Material Center
Philadelphia 12, Pa.

1

Chief
Bureau of Naval Weapons
Department of the Navy
ATTN: RRMA-54
Washington, D. C. 20360

1

Commander
U. S. Naval Ordnance Test Station
ATTN: Technical Library Branch
China Lake, California

1

Commander
U. S. Naval Research Laboratory
ATTN: Technical Information Center
Anacostia Station
Washington 25, D. C.

1

Commander
Mare Island Naval Shipyard
ATTN: Rubber Laboratory
Vallejo, California

1

D. Department of the Air Force

U. S. Air Force Directorate of Research
and Development
ATTN: Lt Col J. B. Shipp, Jr.
Room 4D-313, The Pentagon
Washington 25, D. C.

1

DISTRIBUTION

No. of Copies

Commander
Wright Air Development Division
ATTN: ASRCEE-1 1
 WWRCO 1
 Materials Central 1
Wright-Patterson Air Force Base, Ohio 45433

ARDC Flight Test Center
ATTN: Solid Systems Division, FTRSC
Edwards Air Force Base, California 1

Commander
AMC Aeronautical Systems Center
ATTN: Manufacturing & Materials
 Technology Division, LMBMO
Wright-Patterson Air Force Base, Ohio 45433 2

Commanding Officer
Brookley Air Force Base
ATTN: Air Force Packaging Laboratory
Alabama 1

E. Other Government Agencies

Scientific & Technical Information Facility
ATTN: NASA Representative (SAK/DL) 1
 Mr. B. G. Achhammer 1
 Mr. G. C. Deutsch 1
 Mr. R. V. Rhode 1
P. O. Box 33
College Park, Md. 20740

George C. Marshall Space Flight
ATTN: M-S&M-M 1
 M-F&AE-M 1
Huntsville, Alabama 35800

Scientific Information Office
Defense Research Staff
British Embassy
ATTN: Mr. Francis C. Bruce
Washington, D. C. 20008 3

Canadian Army Staff, Washington
c/o Canadian Liaison Office
(AMCGS-LN-C) ATTN: Major P. A. Tuck
U. S. Army Materiel Command
Washington, D. C. 20315 3

DISTRIBUTION

No. of Copies

Military Attache
Australian Embassy
ATTN: Lt Col D.R.O. Cowey
2001 Connecticut Avenue, N. W.
Washington, D. C.

3

Unclassified

Security Classification

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Rock Island Arsenal Research & Engineering Division Rock Island, Illinois 61201		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3. REPORT TITLE COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS (U)		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Interim Technical Report		
5. AUTHOR(S) (Last name, first name, initial) Williams, John A.		
6. REPORT DATE January 1966	7a. TOTAL NO. OF PAGES 20	7b. NO. OF REFS 0
8a. CONTRACT OR GRANT NO.	9a. ORIGINATOR'S REPORT NUMBER(S) RIA 66-382	
b. PROJECT NO. DA 1C024401A329		
c. AMS Code 5025.11.295	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.		
10. AVAILABILITY/LIMITATION NOTICES Distribution of this document is unlimited.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Rock Island Arsenal	
13. ABSTRACT A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery. Several coagents evaluated with high levels (6 pphr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pphr) of peroxide produced vulcanizates with improved elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone. (U) (Author)		

Unclassified
Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Elastomers Urethane Properties Coagents Curatives Compression Set						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

AD Rock Island Arsenal Laboratory, Rock Island, Illinois COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS, By John A. Williams RIA Lab. Rep. 66-382, Jan 66, 20 p., incl. tables, (DA Project No. 1CO24401A329, AMS Code 5025.11.295) Unclassified report.	UNCLASSIFIED	AD Rock Island Arsenal Laboratory, Rock Island, Illinois COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS, By John A. Williams RIA Lab. Rep. 66-382, Jan 66, 20 p., incl. tables, (DA Project No. 1CO24401A329, AMS Code 5025.11.295) Unclassified report.	UNCLASSIFIED
A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery. Several coagents evaluated with high levels (6 pp/hr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pp/hr) of peroxide produced vulcanizates with improved (Cont.) over	1. Elastomers 2. Urethane 3. Properties 4. Coagents 5. Curatives 6. Compression Set DISTRIBUTION: Copies obtainable from DDC	A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery. Several coagents evaluated with high levels (6 pp/hr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pp/hr) of peroxide produced vulcanizates with improved (Cont.) over	1. Elastomers 2. Urethane 3. Properties 4. Coagents 5. Curatives 6. Compression Set DISTRIBUTION: Copies obtainable from DDC
AD Rock Island Arsenal Laboratory, Rock Island, Illinois COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS, By John A. Williams RIA Lab. Rep. 66-382, Jan 66, 20 p., incl. tables, (DA Project No. 1CO24401A329, AMS Code 5025.11.295) Unclassified report.	UNCLASSIFIED	AD Rock Island Arsenal Laboratory, Rock Island, Illinois COAGENTS FOR IMPROVED ELASTIC RECOVERY IN POLYESTER URETHANE ELASTOMERS, By John A. Williams RIA Lab. Rep. 66-382, Jan 66, 20 p., incl. tables, (DA Project No. 1CO24401A329, AMS Code 5025.11.295) Unclassified report.	UNCLASSIFIED
A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery. Several coagents evaluated with high levels (6 pp/hr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pp/hr) of peroxide produced vulcanizates with improved (Cont.) over	1. Elastomers 2. Urethane 3. Properties 4. Coagents 5. Curatives 6. Compression Set DISTRIBUTION: Copies obtainable from DDC	A number of chemicals were evaluated as coagents in the peroxide vulcanization of polyester urethanes to determine their ability to produce vulcanizates with good elastic recovery. Several coagents evaluated with high levels (6 pp/hr) of peroxide produced vulcanizates with improved elastic recovery compared with vulcanizates crosslinked with high peroxide alone. Tensile strength was unaffected while modulus and hardness increased and elongation decreased. Certain coagents when evaluated with low levels (3 pp/hr) of peroxide produced vulcanizates with improved (Cont.) over	1. Elastomers 2. Urethane 3. Properties 4. Coagents 5. Curatives 6. Compression Set DISTRIBUTION: Copies obtainable from DDC

elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone.

elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone.

elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone.

elastic recovery and only slightly decreased tensile strength compared with vulcanizates cured with high peroxide alone.